

EXTRA HIGH STRENGTH STRUCTURAL PLATE

WELDOX 900 is a general structural steel with a minimum yield strength of 900 N/mm² intended for applications where its high strength permits weight savings to be made. The plate has very good cold bending properties and very good weldability. WELDOX 900 can be obtained with guaranteed impact toughness at temperatures down to -60°C (-76°F). WELDOX 900 totally fulfils the requirements on the corresponding steel grades and qualities according to EN 10 137 part 1 and 2.

APPLICATIONS	Dumptrucks, loaders, industrial trucks, excavators, bulldozers, forestry machines, buckets, cranes, lifting equipment etc.															
DESIGNATION	WELDOX 900 D with impact testing at -20°C (-4 °F). Corresponds to S 890 Q WELDOX 900 E with impact testing at -40°C (-40 °F). Corresponds to S 890 QL WELDOX 900 F with impact testing at -60°C (-76 °F). Corresponds to S 890 QL1															
CHEMICAL COMPOSITION (ladle analysis)	C*	Si*	Mn*	P	S	B*	Nb*	Cr*	V*	Cu*	Ti*	Al*	Mo*	Ni*	N	CEV typical value ¹⁾
	max	max	max	max	max	max	max	max	max	max	max	total min	max	max	max	%
	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
	0,20	0,50	1,60	0,020	0,010	0,005	0,04	0,70	0,06	0,30	0,04	0,018	0,70	2,0	0,015	0,56
	¹⁾ CEV typical value, for information ^{*)} Intentional alloying elements.															
MECHANICAL PROPERTIES	Plate thickness mm		Yield strength R _{0,02} min N/mm ²			Tensile strength R _m N/mm ²			Elongation ¹⁾ A ₅ min A ₅₀ min ²⁾ % %							
	4–50 (50)–80		900 830			940–1100 880–1100			12 16 12 16							
	¹⁾ For transverse test pieces. Values for longitudinal test pieces are 2 units higher. ²⁾ Testing by agreement.															
IMPACT PROPERTIES	Minimum values of impact energy for tests on transverse ¹⁾ and Charpy V test pieces. Minimum values of impact energy in J at test temperatures ²⁾ in °C															
	Steel grade	0	-20	-40	-60											
	WELDOX 900 D	30	27	–	–											
	WELDOX 900 E	35	30	27	–											
	WELDOX 900 F	40	35	30	27											
	¹⁾ Unless otherwise agreed, transverse impact testing according to EN 10 137 option 3 will apply. If only longitudinal impact testing shall apply, it has to be specified in the order. ²⁾ If the test temperature is not specified, the test will be carried out at the lowest test temperature.															
TESTING	Testing in accordance with EN 10 137-1 and EN 10 137-2.															
DELIVERY CONDITION	Quenched and tempered, Q.															
DIMENSIONS	WELDOX 900 is supplied in plate thicknesses of 4–80 mm. More detailed information on dimensions is provided in our brochure E-40. Certain width restrictions may apply. Plate thicker than 80 mm only after specific agreement.															
TOLERANCES	According to EN 10 029. – Tolerances on thickness according to Class A. – Tolerances on flatness according to Class N. (Normal tolerances)															
SURFACE FINISH	According to EN 10 163-2. – Requirements according to Class A. – Repair conditions according to Subclass 1. Repair by welding is allowed, option 14 according to EN 10 137-2.															

**GENERAL TECHNICAL
DELIVERY REQUIREMENTS**

According to our brochure En-40, General Product Information.
WELDOX 900 conforms to all technical requirements of S890 in EN 10 137-2.
Option 3 and 14 are applied.

**HEAT TREATMENT
AND FABRICATION**

WELDOX 900 has obtained its mechanical properties by a quenching and tempering process.
The mechanical properties can not be retained after PWHT at temperatures above 550°C (1020°F).
WELDOX 900 is not suited for applications requiring hot working at temperatures above 550°C
(1020°F) since the material may then lose its good properties.

For information concerning welding and fabrication, see our brochures listed below or consult our
Technical Customer Service.

Fabrication	Brochure No:
Drilling	
Countersinking	
Tapping	En-10

Flame Cutting	
Welding	En-11

Bending	
Shearing	En-12

Turning	
Milling	En-13

Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise
working on the product. Grinding, especially of primer coated plates, may produce dust with high
particle concentration. Our Technical Customer Service Department will provide further information
on request.